

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C08F 4/02, 4/605, 10/00	A1	(11) International Publication Number: WO 95/10542 (43) International Publication Date: 20 April 1995 (20.04.95)
<p>(21) International Application Number: PCT/US94/10178</p> <p>(22) International Filing Date: 9 September 1994 (09.09.94)</p> <p>(30) Priority Data: 08/138,818 15 October 1993 (15.10.93) US</p> <p>(71) Applicant: EXXON CHEMICAL PATENTS INC. [US/US]; 5200 Bayway Drive, Baytown, TX 77520 (US).</p> <p>(72) Inventor: JEJLOWO, Moses, Olukayode; 3410 Park Springs Lane, Kingwood, TX 77345 (US).</p> <p>(74) Agents: SHER, Jaimes; Exxon Chemical Company, P.O. Box 2149, Baytown, TX 77522-2149 (US) et al.</p>		<p>(81) Designated States: CA, JP, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).</p> <p>Published <i>With international search report.</i></p>
<p>(54) Title: POLYMERIZATION CATALYST SYSTEMS, THEIR PRODUCTION AND USE</p> <p>(57) Abstract</p> <p>The invention is generally directed toward a supported catalyst system useful for polymerizing olefins. The method for forming the catalyst system of the invention provides for supporting a bulky ligand transition metal compound on a carrier and separately supporting a cocatalyst or activator for the bulky compound. The bulky ligand transition metal compound of the invention can be a metallocene. The metallocene catalyst systems of the invention have unexpectedly high activity as compared with most catalysts systems previously described where the metallocene and activator are on one carrier. The invention provides for the ability to manipulate the catalyst system easily by varying the quantities of the individually supported components of the invention. Until now previous catalyst system had to be reformulated from scratch, which is expensive and time consuming. Additionally it is now possible with catalyst systems of the invention to conveniently change the catalyst system, by adjusting the catalyst to activator ratio in a continuous polymerization process, particularly in gas phase process and to allow for quicker transitioning periods between polymer grades.</p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

- 1 -

**POLYMERIZATION CATALYST SYSTEMS, THEIR PRODUCTION
AND USE**

FIELD OF THE INVENTION

5 This invention relates to catalysts, catalyst systems and to methods for their production and use in olefin polymerization. The invention particularly relates to a catalyst system of a supported bulky ligand transition metal compound and separately supported activator useful for the polymerization of olefins.

BACKGROUND OF THE INVENTION

10 A new catalyst technology has developed which provides for the modification and/or control over the properties and characteristics of a polymer. This technology principally involves the use of single-site catalysts to produce a broad range of polymers generally having a narrow molecular weight distribution and a narrow composition distribution. These catalysts are generally in the field of
15 transition metal catalysis. The art has focused on the type of catalyst and catalyst system employed and methods for their manufacture and use in polymerization catalysis.

 It is desirable in many polymerization processes, particularly a gas phase process, to use a supported catalyst. Generally these catalyst systems include a
20 metallocene and alumoxane supported on the same carrier, such as silica, and subsequently dried to a powder. For example, U.S. Patent No. 4,937,217 generally describes a mixture of trimethylaluminum and triethylaluminum added to an undehydrated silica then adding a metallocene to form a dry catalyst. EP-308177-B1 generally describes adding a wet monomer to a reactor containing a
25 metallocene, trialkylaluminum and undehydrated silica. U.S. Patent Nos. 4,912,075, 4,935,937 and 4,937,301 generally relate to adding trimethylaluminum to an undehydrated silica and then adding a metallocene to form a dry supported catalyst. Similarly, U.S. Patent Nos. 5,008,228, 5,086,025 and 5,147,949 generally describe forming a dry supported catalyst by the addition of
30 trimethylaluminum to a water impregnated silica then adding the metallocene. U.S. Patent No. 4,914,253 describes adding trimethylaluminum to undehydrated silica, adding a metallocene and then drying the catalyst with an amount of hydrogen to produce a polyethylene wax. U.S. Patent Nos. 4,808,561, 4,897,455 and 4,701,432 describe techniques to form a supported catalyst where the inert carrier,
35 typically silica, is calcined and contacted with a metallocene(s) and a activator/cocatalyst component. U.S. Patent No. 5,238,892 describes forming a

- 2 -

dry supported catalyst by mixing a metallocene with an alkyl aluminum then adding undehydrated silica. U.S. Patent No, 5,240,894 generally pertains to forming a supported metallocene/alumoxane catalyst system by forming a metallocene/alumoxane reaction solution, adding a porous carrier, evaporating the
5 resulting slurry to remove residual solvent from the carrier. These references all concern the combination of a metallocene and alumoxane on one support or hydrolyzing an aluminum alkyl in situ on one support with a metallocene catalyst compound.

It would be highly desirable to have a polymerization catalyst system that
10 could be modified easily without having to reformulate the entire catalyst system. Thus, a need exists in industry for an improved polymerization catalyst system and method for producing such a catalyst system.

SUMMARY OF THE INVENTION

This invention is generally directed towards a new polymerization catalyst
15 system and to methods for its manufacture.

In one embodiment, the invention provides for a catalyst system comprising at least one first component comprising a majority of at least one supported bulky ligand transition metal compound and at least one second component comprising a majority of at least one supported cocatalyst or activator for said compound.

20 In another embodiment of the invention, there is provided a process for producing polyolefins by contacting olefin monomer, optionally with comonomer in the presence of the catalyst system described above.

In yet another embodiment of the invention, a method for producing the catalyst system described above is provided.

25 It is an object of the invention to provide a catalyst system with increased activity. It is a related object of the invention to provide a catalyst system capable of producing polymers with high molecular weights and lower melt indices. A further object of the invention is to provide a catalyst system that is easily adaptable to a gas phase process. Another object of the invention is to provide a
30 catalyst system that is easily modified or tailored. Yet another object of the invention is to provide a simple catalyst system that is cost effective and efficient.

DETAILED DESCRIPTION OF THE INVENTION

Introduction

This invention is generally directed toward a supported catalyst system
35 useful for polymerizing olefins. The method for forming the catalyst system of the invention provides for supporting a bulky ligand transition metal compound on a

- 3 -

carrier and separately supporting a cocatalyst or activator for the bulky compound. The bulky ligand transition metal compound of the invention can be a metallocene. The metallocene catalyst systems of the invention have unexpectedly high activity as compared with most catalysts systems previously described where the

5 metalocene and activator are on one carrier. The invention provides for the ability to manipulate the catalyst system easily by varying the quantities of the individually supported components of the invention. Until now previous catalyst system had to be reformulated from scratch, which is expensive and time consuming. Additionally it is now possible with catalyst systems of the invention to conveniently change the


10 catalyst system, by adjusting the catalyst to activator ratio in a continuous polymerization process, particularly in gas phase process and to allow for quicker transition periods between polymer grades.

Catalyst Systems and Methods For Their Production

The catalyst is preferably a bulky ligand transition metal compound. The

15 bulky ligand may contain a multiplicity of bonded atoms, preferably carbon atoms, forming a group which may be cyclic with one or more optional heteroatoms. The bulky ligand may be a cyclopentadienyl derivative which can be mono- or poly-nuclear. One or more bulky ligands may be bonded to the transition metal atom. The transition metal atom may be a Group 4, 5 or 6 transition metal. Other ligands

20 may be bonded to the transition metal, preferably detachable by a cocatalyst such as a hydrocarbyl or halogen leaving group. The catalyst is derivable from a compound of the formula



wherein L is the bulky ligand; X is the leaving group, M is the transition metal and

25 m and n are such that the total ligand valency corresponds to the transition metal valency. Preferably the catalyst is four co-ordinate such that the compound is ionizable to a 1⁺ charge state.

The ligands L and X may be bridged to each other and if two ligands L and/or X are present, they may be bridged. The metallocenes may be full-sandwich

30 compounds having two or more ligands L which are cyclopentadienyl ligands or cyclopentadiene derived ligands or half-sandwich compounds having one ligand L only which is a cyclopentadienyl ligand or derived ligand.


The metallocene compounds contain a multiplicity of bonded atoms, preferably carbon atoms, and typically contain a cyclic structure such as, for

35 example, a cyclopentadienyl ligand, substituted or unsubstituted, or cyclopentadienyl derived ligand or any other ligand capable of η-5 bonding to the

- 4 -

transition metal atom. One or more bulky ligands may be π -bonded to the transition metal atom. The transition metal atom may be a Group 4, 5 or 6 transition metal and/or a metal from the lanthanide and actinide series. Other ligands may be bonded to the transition metal, such as a leaving group, such as but not limited to hydrocarbyl, hydrogen or any other univalent anionic ligand.. Non-limiting examples of metallocene catalysts and catalyst systems are discussed in for example, U.S. Patent Nos. 4,530,914, 4,952,716, 5,124,418, 4,808,561, 4,897,455, 5,278,119, 5,304,614 all of which are herein fully incorporated by reference. Also, the disclosures of EP-A- 0129,368, EP-A-0520732, EP-A-0420436, WO 91/04257 WO 92/00333, WO 93/08221, and WO 93/08199 are all fully incorporated herein by reference.

For the purposes of this patent specification the term "metallocene" is defined to contain one or more cyclopentadienyl moiety in combination with a transition metal of the Periodic Table of Elements. In one embodiment the metallocene catalyst component is represented by the general formula $(Cp)_mMR_nR'_p$ wherein Cp is a substituted or unsubstituted symmetrically or unsymmetrically cyclopentadienyl ring; M is a Group 4, 5 or 6 transition metal; R and R' are independently selected halogen, hydrocarbyl group, or hydrocarboxyl groups having 1-20 carbon atoms; $m = 1-3$, $n = 0-3$, $p = 0-3$, and the sum of $m + n + p$ equals the oxidation state of M , where $m = 2$, two Cp 's can be bridged with a carbon, germanium, silicon, phosphorous or a nitrogen atom. In another embodiment the metallocene catalyst component is represented by the formulas:



wherein M is a Group 4, 5, 6 transition metal, $C_5R'_m$ is an unsubstituted and/or a symmetrically or unsymmetrically substituted cyclopentadienyl, each R' , which can be the same or different is hydrogen alkyl, alkenyl, aryl, alkylaryl or arylalkyl radical having from 1 to 20 carbon atoms or two carbon atoms joined together to form a part of a C_4 to C_{20} ring, R'' is one or more of or a combination of a carbon, a germanium, a silicon, a phosphorous or a nitrogen atom containing radical substituting on and bridging two $(C_5R'_m)$ rings, or bridging one $(C_5R'_m)$ ring back to M , when $p = 0$ and $x = 1$ otherwise "x" is always equal to 0, each Q which can be the same or different is an aryl, alkyl, alkenyl, alkylaryl, or arylalkyl radical having from 1 to 20 carbon atoms or halogen, Q' is an alkylidene radical having from 1-20 carbon atoms, s is 0 or 1 and when s is 0, m is 5 and p is 0, 1 or 2 and when s is 1, m is 4 and p is 1.

- 5 -

Various forms of the catalyst system of the metallocene type may be used in the polymerization process of this invention. Exemplary of the development of metallocene catalysts in the art for the polymerization of ethylene is the disclosure of U.S. Patent No. 4,871,705, 4,937,299, 5,017,714 and 5,120,867, all of which are fully incorporated herein by reference for U.S. patent practice. These publications teach the structure of the metallocene catalysts and include alumoxane as the cocatalyst. None of these references disclose the catalyst system of this invention. There are a variety of methods for preparing alumoxane, for examples see U.S. Patent Nos. 4,665,208, 4,952,540 and 5,103,031, incorporated herein by reference for U.S. patent practice.

For the purposes of this patent specification, the terms "cocatalysts or activators" are used interchangeably and are defined to be any compound or component which can activate a bulky ligand transition metal compound or a metallocene catalyst component. In one embodiment the activators generally contain a metal of Group 1 and 3 of the Periodic Table of Elements. In the preferred embodiment the bulky transition metal compound are metallocenes, which are activated by trialkylaluminum compounds, alumoxanes both linear and cyclic, or ionizing ionic activators or compounds such as tri (n-butyl) ammonium tetra (pentafluorophenyl) boron, which ionize the neutral metallocene compound. Such ionizing compounds may contain an active proton, or some other cation associated with but not coordinated or only loosely coordinated to the remaining ion of the ionizing ionic compound. Such compounds are described in PCT Application WO 93/11172 and EP-A-0520 732, EP-A-500 944, EP-A-0 277 003 and EP-A-0 277 004 published August 3, 1988, and U.S. Patent Nos. 5,153,157, 5,198,401, 5,241,025, and 5,278,119, are all herein fully incorporated by reference. Further, the metallocene catalyst component can be a monocyclopentadienyl heteroatom containing compound. This heteroatom is activated by either an alumoxane or an ionic activator to form an active polymerization catalyst system to produce polymers useful in this present invention. These types of catalyst systems are described in, for example, PCT International Publication WO 92/00333 published January 9, 1992, U.S. Patent Nos. 5,057,475, 5,096,867, 5,055,438 and 5,227,440 and EP-A-0 420 436, WO 91/ 04257, all of which are fully incorporated herein by reference. In addition, the metallocene catalysts useful in this invention can include non-cyclopentadienyl catalyst components, or ancillary ligands such as boroles or carbolides in combination with a transition metal. Additionally it is not beyond the scope of this

- 6 -

invention that the catalysts and catalyst systems may be those described in U.S. Patent No. 5,064,802 and PCT publications WO 93/08221 and WO 93/08199 published April 29, 1993 all of which are herein incorporated by reference. All the catalyst systems of the invention may be, optionally, prepolymerized or used in conjunction with an additive or scavenging component to enhance catalytic productivity.

For purposes of this patent specification the term "carrier" or "support" can be any porous support such as talc, inorganic oxides, and resinous support materials such as polyolefin or polymeric compounds. Suitable inorganic oxide materials which are desirably employed include from the Periodic Table of Elements Groups 2, 3, 4 or 5 metal oxides such as silica, alumina, silica-alumina, and mixtures thereof. Other inorganic oxides that may be employed either alone or in combination with the silica, alumina or silica-alumina are magnesia, titania, zirconia, and the like. Other suitable support materials can be employed such as, finely divided polyolefins, such as polyethylene or polymeric compounds. The specific particle size of the support or inorganic oxide, surface area, pore volume, and number of hydroxyl groups are not critical to its utility in the practice of this invention. However, such characteristics determine the amount of support to be employed in preparing the catalyst compositions, as well as affecting the properties of polymers formed. The characteristics of the carrier or support must therefore be taken into consideration in choosing the same for use in the particular invention. In one embodiment the carrier is surface modified with surface modifying agents as described in U.S. Patent No. 5,124,418 incorporated herein by reference.

The catalyst system of this invention can be made in various ways. In one embodiment, a bulky ligand transition metal compound, such as a metallocene as described above, is contacted with a first carrier to form a first component, and independently, a cocatalyst or activator, such as an alumoxane or ionic activator, is contacted with a second carrier to form a second component. The first and second components can be used in slurry form or dried or any combination thereof.

The first component of the catalyst system of the invention comprises a majority of a carrier and a bulky ligand transition metal compound. The bulky ligand transition metal compound is generally in the range of 0.01 to about 50 weight percent of the total weight of the first component, preferably, 0.1 to about 25 weight percent, more preferably 0.3 to 10 weight percent and most preferably 0.5 to about 5 weight percent.

- 7 -

The second component of the catalyst system of the invention comprises a majority of a carrier and a cocatalyst or activator. The cocatalyst or activator is generally in the range of 1 to about 75 weight percent of the total weight of the second component, preferably, 1 to about 50 weight percent, more preferably 1 to about 25 weight percent, and most preferably 1 to about 15 weight percent.

The carriers of the invention can be the same or different or mixtures thereof. In the preferred embodiment the carrier in both components is the same type, and is preferably silica.

In another embodiment, two or more metallocenes can be used to form the first component or more than one first component is used and a similar or different activator can be used on one second component or more than one second component containing one or more activator can be used in the invention, or any combination thereof. In still yet another embodiment, the first and second components are further supported together on another carrier, other than the carriers used to support the first and second components, or separately supported on different carriers or even different types of carriers.

In one embodiment of the invention the first component can contain a quantity of an activator such that the mole ratio of the transition metal of the bulky ligand transition metal compound to the metal of the activator is in the range of less than 0.2:1 to 1000:1, preferably, less than 0.5:1 to 500:1, more preferably 0.7:1 to 300:1 and most preferably less than 1:1 to 100:1.

In another embodiment the second component can contain a quantity of a bulky ligand transition metal compound such that the mole ratio of the metal of the activator to the transition metal of the bulky compound is in the range of less than 0.2:1 to 1000:1, preferably, less than 0.5:1 to 500:1, more preferably 0.7:1 to 300:1 and most preferably less than 1:1 to 100:1.

In another embodiment, the mole percent of the metal of the activator of the second component to the transition metal of the bulky ligand transition metal compound of the first component is in the range of 1000:1 to 50:1, preferably less than 500:1, more preferably 200:1, even more preferably 150:1 and most preferably 50:1 to 100:1.

In a preferred embodiment, the weight ratio of the first component to the second component is in the range of 20:1 to about 1:20, preferably 10:1 to 10:1, more preferably 5:1 to 1:5 and most preferably 2:1 to 1:2.

Polymerization Process

- 8 -

5 The catalyst system of this invention is particularly well suited for the polymerization of monomers and optionally comonomers in any polymerization or prepolymerization process, gas, slurry or solution phase; even a high pressure autoclave process can be utilized. In the preferred embodiment a gas phase process is utilized.

10 In the preferred embodiment, this invention is directed toward the gas phase polymerization or copolymerization reactions involving the polymerization or optionally prepolymerization of one or more of the alpha-olefin monomers having from 2 to 20 carbon atoms, preferably 2-12 carbon atoms. The invention is particularly well suited to the copolymerization reactions involving the polymerization of one or more of the monomers, for example alpha-olefin monomers of ethylene, propylene, butene-1, pentene-1, 4-methylpentene-1, hexene-1, octene-1, decene-1 and cyclic olefins such as styrene. Other monomers can include polar vinyl, dienes, norbornene, acetylene and aldehyde monomers.

15 Preferably a copolymer of ethylene or propylene is produced such that the amount of ethylene or propylene and comonomer is adjusted to produce a desired polymer product. Preferably the comonomer is an alpha-olefin having from 3 to 15 carbon atoms, preferably 4 to 12 carbon atoms and most preferably 4 to 10 carbon atoms. In another embodiment ethylene is polymerized with at least two comonomers to

20 form a terpolymer and the like.

In one embodiment of the process of the invention, the olefin(s) are prepolymerized in the presence of the catalyst system of the invention prior to the main polymerization. The prepolymerization can be carried out batchwise or continuously in gas, solution or slurry phase including at elevated pressures. The prepolymerization can take place with any alpha-olefin monomer or combination and/or in the presence of any molecular weight controlling agent such as hydrogen. For details on prepolymerization see U.S. Patent No. 4,923,833 and 4,921,825 and EP-B-0279 863, all of which are incorporated fully herein by reference for purposes of U.S. practice.

30 Typically in a gas phase polymerization process a continuous cycle is employed where in one part of the cycle, of a reactor, a cycling gas stream, otherwise known as a recycle stream or fluidizing medium, is heated in the reactor by the heat of polymerization. This heat is removed in another part of the cycle by a cooling system external to the reactor.

35 Generally in a gas fluidized bed process for producing polymer from monomers a gaseous stream containing one or more monomers is continuously

- 9 -

cycled through a fluidized bed in the presence of a catalyst under reactive conditions. The gaseous stream is withdrawn from the fluidized bed and recycled back into the reactor. Simultaneously, polymer product is withdrawn from the reactor and new or fresh monomer is added to replace the polymerized monomer.

5 The catalyst is introduced into the reactor via a catalyst feeder mechanism either continuously or intermittently as is known in the art. Usually the catalyst is contained in a vessel with a mechanism for controlling the quantity of catalyst to be injected into the reactor. Typically the catalyst is blown into the reactor with a gas such as nitrogen. Many times these systems have multiple catalyst feeders and
10 injection points for introducing catalyst into a reactor.

 The invention provides for a process for polymerization of olefins alone or in combination with one or more other olefins in a reactor, said process comprising polymerization in the presence of a catalyst system which is introduced into said reactor, said catalyst system comprising (a) at least one first component comprising
15 at least one first carrier and at least one bulky ligand transition metal compound supported on said first carrier and (b) at least one second component comprising at least one second carrier and at least one cocatalyst or activator for said bulky ligand transition metal compound supported on said second carrier..

 In one embodiment of the invention components (a) and (b) are introduced
20 into the reactor simultaneously from the same or different catalyst feeder. In another embodiment components (a) and (b) are introduced into the reactor together or apart. In still yet another embodiment components (a) and (b) are introduced into the reactor mixed together.

 It is also contemplated in an alternative embodiment that the first
25 component could comprise a mixture of a bulky ligand transition metal compound and a traditional Ziegler-Natta catalyst compound, other non-bulky ligand transition metal compound, or non-metallocene compound. Non-limiting examples of traditional Ziegler-Natta catalyst compounds are described in U.S. Patent Nos. 4,086,408, 4,302,565, 4,988,783 and 4,427,573. Thus, the same is true for the
30 activator component of the invention which could include any activator for the traditional Ziegler-Natta catalyst or non-metallocene compound alone or in combination with those activators and catalysts previously described.

EXAMPLES

- 10 -

In order to provide a better understanding of the present invention including representative advantages and limitations thereof, the following examples are offered.

Example 1

5 Preparation of Silica-Supported Cp_2ZrCl_2

10 g sample of Davison 948 silica dehydrated at 850°C was suspended in 60 cm³ hexane at 22°C. A solution of 0.331 g Cp_2ZrCl_2 in 20 cm³ toluene was then added slowly. After 1 h, the solvent was removed under vacuum to give a free-flow supported metallocene.

10 Preparation of TMA-Treated Silica Support

400 g Davison 948 silica having Loss-On-Ignition (LOI) value of 11.14 wt-% was added slowly to 3380 cm³ of 10 wt-% trimethyl aluminum solution in iso-pentane contained in a 5-liter flask at -75°C. The silica was added at a rate of about 1.1 g/min. After all the silica had been added the slurry was allowed to
15 warm up to 22°C and this was maintained for 1 h. Then the support material was dried to free-flowing powder.

Polymerization of Olefins

0.35 g sample of the TMA-treated silica described above was added into a catalyst holding tube as a bottom layer of treated silica, to this was added 0.2 g of
20 the silica-supported Cp_2ZrCl_2 described above, then a second layer of 0.35 g of the TMA-treated silica was added as a top layer such that the silica-supported metallocene was sandwiched between two layers of the TMA-treated silica. This catalyst holding tube was, meanwhile, clamped in place such that no shaking took place. This catalyst setup was then admitted into a semi-batch gas-phase reactor with a N₂ pressure. A feed of 1-butene in ethylene was then admitted into the
25 reactor at 85°C. The pressure in the reactor was held constant by continuously feeding 5 mol-% 1-butene in ethylene to compensate for any pressure change due to polymerization. After 0.5 h, the polymer formed was separated from the seed bed material and analyzed for resin molecular properties and the results are shown
30 in Table 1.

Example 2

Preparation of Silica-Supported Cp_2ZrMe_2

10 g sample of Davison 948 silica dehydrated to 850°C was suspended in 60 cm³ hexane at 22°C. A solution of 0.283 g Cp_2ZrMe_2 in 20 cm³ toluene was
35 then added slowly. After 1 h, the solvent was removed under vacuum to give a free-flow supported metallocene.

- 11 -

0.35 g sample of the TMA-treated silica described in Example 1 was added into a catalyst holding tube as a bottom layer of treated silica, to this was added 0.2 g of the silica-supported Cp_2ZrMe_2 described above, then a second layer of 0.35 g of the TMA-treated silica was added as a top layer such that the silica-supported metallocene was sandwiched between two layers of the TMA-treated silica. This catalyst holding tube was, meanwhile, clamped in place such that no shaking took place. This catalyst setup was then admitted into a semi-batch gas-phase reactor that had been pretreated with 0.13 cm^3 of 24.7 wt-% triethylaluminum and tested for the polymerization of ethylene/1-butene as described in Example 1; the results are summarized in Table 1.

Example 3

Preparation of Silica-Supported Cp_2HfCl_2

11.3 g sample of Davison 948 silica dehydrated to 850°C was suspended in 60 cm^3 hexane at 22°C . A solution of 0.246 g Cp_2HfCl_2 in 20 cm^3 toluene was then added slowly. After 1 h, the solvent was removed under vacuum to give a free-flow supported metallocene. 1 g sample of this supported metallocene was mixed uniformly in a vial with 3 g sample of the TMA-treated silica described in Example 1. 0.9 g sample of this mixture was then admitted into a semi-batch gas-phase reactor with a N_2 pressure and tested for the polymerization of ethylene/1-butene as described in Example 1; the results are summarized in Table 1.

Example 4

Preparation of Silica-Supported Cp_2HfCl_2

0.5 g sample of the supported metallocene described in Example 3 above was mixed uniformly in a vial with 2.5 g sample of the TMA-treated silica described in Example 1. 1 g sample of this mixture was then admitted into a semi-batch gas-phase reactor with a N_2 pressure and tested for the polymerization of ethylene/1-butene as described in Example 1; the results are summarized in Table 1.

Example 5

Preparation of Silica-Supported ($n\text{PrCp}_2\text{ZrCl}_2$)

10 g sample of Davison 948 silica dehydrated to 850°C was suspended in 60 cm^3 hexane at 22°C . A solution of 0.43 g ($n\text{PrCp}_2\text{ZrCl}_2$) in 20 cm^3 toluene was then added slowly. After 1 h, the solvent was removed under vacuum to give a free-flow supported metallocene.

0.35 g sample of the TMA-treated silica described in Example 1 was added into a catalyst holding tube as a bottom layer of treated silica, to this was added

- 12 -

0.1 g of the silica-supported ($^n\text{PrCp}_2\text{ZrCl}_2$) described above, then a second layer of 0.35 g of the TMA-treated silica was added as a top layer such that the silica-supported metallocene was sandwiched between two layers of the TMA-treated silica. This catalyst holding tube was, meanwhile, clamped in place such that no shaking took place. This catalyst setup was then admitted into a semi-batch gas-phase reactor with N_2 and tested for the polymerization of ethylene/1-butene as described in Example 1; the results are summarized in Table 1.

Example 6

0.25 g sample of the TMA-treated silica described in Example 1 was added into a catalyst holding tube as a bottom layer of treated silica, to this was added 0.04 g of the silica-supported ($^n\text{PrCp}_2\text{ZrCl}_2$) described in Example 5 above, then a second layer of 0.25 g of the TMA-treated silica was added as a top layer such that the silica-supported metallocene was sandwiched between two layers of the TMA-treated silica. This catalyst holding tube was, meanwhile, clamped in place such that no shaking took place. This catalyst setup was then admitted into a semi-batch gas-phase reactor with N_2 and tested for the polymerization of ethylene/1-butene as described in Example 1; the results are summarized in Table 1.

Example 7

1 g sample of the supported metallocene described in Example 5 above was mixed uniformly in a vial with 2 g sample of the TMA-treated silica described in Example 1. 0.24 g sample of this mixture was then admitted into a semi-batch gas-phase reactor with a N_2 pressure and tested for the polymerization of ethylene/1-butene as described in Example 1; the results are summarized in Table 1.

Example 8

0.32 g sample of Davison 948 silica dehydrated to 850°C was added into a catalyst holding tube as a bottom layer of silica, to this was added 0.16 g of the silica-supported ($^n\text{PrCp}$) $_2\text{ZrCl}_2$ described in Example 5 above, then a second layer of Davison 948 silica dehydrated to 850°C was added as a top layer such that the silica-supported metallocene was sandwiched between two layers of the 850°C -treated silica. This catalyst holding tube was, meanwhile, clamped in place such that no shaking took place. This catalyst setup was then admitted into a semi-batch gas-phase reactor with N_2 and tested for the polymerization of ethylene/1-butene as described in Example 1. Subsequently, 0.7 g of the TMA-treated silica

described in Example 1 was added into the reactor; the results are summarized in Table 1.

Example 9 (Comparative)

Preparation of supported ($n\text{PrCp}$)₂ZrCl₂

- 5 1200 cm³ of a 30 wt-% MAO solution in toluene was added to 680 g of Davison 948 silica dried to 200°C in a 2-gal reactor. Then 2000 cm³ toluene was added. The temperature was raised to 70°C and maintained for 4 h. Then a toluene solution of 16.5 g ($n\text{PrCp}$)₂ZrCl₂ was added slowly followed by a 2 h hold of the reaction conditions. The resultant catalyst was dried to free-flowing powder under reduced pressure. This catalyst had Al/Zr molar ratio of 130 and Zr loading of 0.4 wt-%. A sample of this catalyst was tested for ethylene/1-butene co-polymerization as described in Example 1. The reactor was pretreated with 0.15 cm³ of 24.7 wt-% TEAL in heptane. The results are summarized in Table 1.

Example 10

15 **Preparation of Silica-Supported ($i\text{PrCp}$)₂ZrCl₂**

10 g sample of Davison 948 silica dehydrated to 850°C was suspended in 60 cm³ hexane at 22°C. A solution of 0.43 g ($i\text{PrCp}$)₂ZrCl₂ in 20 cm³ toluene was then added slowly. After 1 h, the solvent was removed under vacuum to give a free-flow supported metallocene.

- 20 0.36 g sample of the TMA-treated silica described in Example 1 was added into a catalyst holding tube as a bottom layer of treated silica, to this was added 0.15 g of the silica-supported ($i\text{PrCp}$)₂ZrCl₂ described above, then a second layer of 0.36 g of the TMA-treated silica was added as a top layer such that the silica-supported metallocene was sandwiched between two layers of the TMA-treated silica. This catalyst holding tube was, meanwhile, clamped in place such that no shaking took place. This catalyst setup was then admitted into a semi-batch gas-phase reactor with N₂ and tested for the polymerization of ethylene/1-butene as described in Example 1; the results are summarized in Table 1.

Example 11 (Comparative)

30 **Preparation of supported ($i\text{PrCp}$)₂ZrCl₂**

- 1415 cm³ of a 30 wt-% MAO solution in toluene was added to 800 g of Davison 948 silica dried to 200°C in a 2-gal reactor. Then 2000 cm³ toluene was added. The temperature was raised to 70°C and maintained for 4 h. Then a toluene solution of 21.7 g ($i\text{PrCp}$)₂ZrCl₂ was added slowly followed by a 2 h hold of the reaction conditions. The resultant catalyst was dried to free-flowing powder under reduced pressure. This catalyst had Al/Zr molar ratio of 110 and Zr loading

- 14 -

of 0.44 wt-%. A sample of this catalyst was tested for ethylene/1-butene co-polymerization as described in Example 1. The reactor was pretreated with 0.15 cm³ of 24.7 wt-% TEAL in heptane. The results are summarized in Table 1.

Example 12

5 Preparation of Silica-Supported (1,3-MeEtCp)₂ZrCl₂

10 g sample of Davison 948 silica dehydrated to 850°C was suspended in 60 cm³ hexane at 22°C. A solution of 0.43 g (1,3-MeEtCp)₂ZrCl₂ in 20 cm³ toluene was then added slowly. After 1 h, the solvent was removed under vacuum to give a free-flow supported metallocene.

10 0.35 g sample of the TMA-treated silica described in Example 1 was added into a catalyst holding tube as a bottom layer of treated silica, to this was added 0.12 g of the silica-supported (1,3-MeEtCp)₂ZrCl₂ described above, then a second layer of 0.35 g of the TMA-treated silica was added as a top layer such that the silica-supported metallocene was sandwiched between two layers of the
15 TMA-treated silica. This catalyst holding tube was, meanwhile, clamped in place such that no shaking took place. This catalyst setup was then admitted into a semi-batch gas-phase reactor with N₂ and tested for the polymerization of ethylene/1-butene as described in Example 1; the results are summarized in Table 1.

20 Example 13 (Comparative)

Preparation of supported (1,3-MeEtCp)₂ZrCl₂

52.3 g of Davison 948 silica dried to 200°C was slurried in 300 cm³ heptane in a reaction flask. The flask was cooled to 0°C and 105 cm³ of 30 wt-% methylalumoxane in toluene was added. After 0.5 h, the temperature was raised to
25 70°C and maintained for 3 h. Then a toluene solution of 1.521 g (1,3-MeEtCp)₂ZrCl₂ as prepared above was added slowly followed by a 1 h hold of the reaction conditions. Then the resultant catalyst was dried to free-flowing powder under reduced pressure. This catalyst had Al/Zr molar ratio of 120 and Zr loading of 0.45 wt-%. A sample of this catalyst was tested for ethylene/1-butene
30 co-polymerization as described in Example 1. The reactor was pretreated with 0.2 cm³ of 24.7 wt-% TEAL in heptane. The results are summarized in Table 1.

Example 14

Preparation of Silica-Supported (1,3-MeⁿBuCp)₂ZrCl₂

10.5 g sample of Davison 948 silica dehydrated to 850°C was suspended
35 in 100 cm³ hexane at 22°C. A solution of 0.203 g (1,3-MeⁿBuCp)₂ZrCl₂ in 20

- 15 -

cm³ toluene was then added slowly. After 1 h, the solvent was removed under vacuum to give a free-flow supported metallocene.

0.3 g sample of the TMA-treated silica described in Example 1 was added into a catalyst holding tube as a bottom layer of treated silica, to this was added
5 0.2 g of the silica-supported (1,3-MeⁿBuCp)₂ZrCl₂ described above, then a second layer of 0.3 g of the TMA-treated silica was added as a top layer such that the silica-supported metallocene was sandwiched between two layers of the TMA-treated silica. This catalyst holding tube was, meanwhile, clamped in place such that no shaking took place. This catalyst setup was then admitted into a semi-
10 batch gas-phase reactor with N₂ and tested for the polymerization of ethylene/1-butene as described in Example 1. The reactor was pretreated with 0.2 cm³ of 24.7 wt-% TEAL in heptane. The results are summarized in Table 1.

Example 15

Preparation of Silica-Supported (1,3-MeⁿBuCp)₂ZrCl₂

15 10 g sample of Davison 948 silica dehydrated to 850°C was suspended in 60 cm³ hexanes at 22°C. A solution of 0.497 g (1,3-MeⁿBuCp)₂ZrCl₂ in 20 cm³ toluene was then added slowly. After 1 h, the solvent was removed under vacuum to give a free-flow supported metallocene.

0.35 g sample of the TMA-treated silica described in Example 1 was added
20 into a catalyst holding tube as a bottom layer of treated silica, to this was added 0.125 g of the silica-supported (1,3-MeⁿBuCp)₂ZrCl₂ described above, then a second layer of 0.35 g of the TMA-treated silica was added as a top layer such that the silica-supported metallocene was sandwiched between two layers of the TMA-treated silica. This catalyst holding tube was, meanwhile, clamped in place
25 such that no shaking took place. This catalyst setup was then admitted into a semi-batch gas-phase reactor with N₂ and tested for the polymerization of ethylene/1-butene as described in Example 1; the results are summarized in Table 1.

Example 16 (Comparative)

Preparation of supported (1,3-MeⁿBuCp)₂ZrCl₂

30 20.6 g of Davison 948 silica dried to 200°C was slurried in 110 cm³ toluene in a reaction flask. The flask was cooled to 0°C and 36.5 cm³ of 30 wt-% methylalumoxane in toluene was added. After 1 h, the temperature was raised to 70°C and maintained for 4 h. Then a toluene solution of 0.742 g (1,3-MeⁿBuCp)₂ZrCl₂ as prepared above was added slowly followed by a 2 h hold of
35 the reaction conditions. Then the resultant catalyst was dried to free-flowing

- 16 -

powder under reduced pressure. This catalyst had Al/Zr molar ratio of 100 and Zr loading of 0.5 wt-%. A sample of this catalyst was tested for ethylene/1-butene co-polymerization as described in Example 1. The reactor was pretreated with 0.2 cm³ of 24.7 wt-% TEAL in heptane. The results are summarized in Table 1.

5 **Example 17**

Preparation of Silica-Supported Me₂Si(THI)₂ZrCl₂

 10 g sample of Davison 948 silica dehydrated to 850°C was suspended in 60 cm³ hexanes at 22°C. A solution of 0.43 g Me₂Si(THI)₂ZrCl₂ racemic dimethyl-1-silanylene bridged bis-(tetrahydroindenyl) zirconium dichloride in 20
10 cm³ toluene was then added slowly. After 1 h, the solvent was removed under vacuum to give a free-flow supported metallocene.

 0.35 g sample of the TMA-treated silica described in Example 1 was added into a catalyst holding tube as a bottom layer of treated silica, to this was added 0.12 g of the silica-supported Me₂Si(THI)₂ZrCl₂ described above, then a second
15 layer of 0.35 g of the TMA-treated silica was added as a top layer such that the silica-supported metallocene was sandwiched between two layers of the TMA-treated silica. This catalyst holding tube was, meanwhile, clamped in place such that no shaking took place. This catalyst setup was then admitted into a semi-
20 batch gas-phase reactor with N₂ and tested for the polymerization of ethylene/1-butene as described in Example 1; the results are summarized in Table 1.

 While the present invention has been described and illustrated by reference to particular embodiments thereof, it will be appreciated by those of ordinary skill in the art that the invention lends itself to variations not necessarily illustrated herein. For example, it is not beyond the scope of this invention to use the
25 polymerization catalyst of the invention in two or more reactors or to control a polymerization process by manipulating the components of catalyst system of the invention. For this reason, then, references should be made solely to the appended claims for purposes of determining the true scope of the present invention.

Table 1

Example	Run Length (min)	Monomer Pressure (psi)	Yield (g)	Normalized Catalyst Efficiency ¹	I _{2,1} (dg/min)	I _{2,1} (dg/min)	Density (g/cc)	Mw	Comments
1	30	96	52	813	6.77	180.1	0.9361	61500	Cp ₂ ZrCl ₂
2	60	146	149	745	1.93	44.8	0.9238	83270	Cp ₂ ZrMe ₂
3	60	183	25	91	-	2.0	0.9321	198400	Cp ₂ HfCl ₂
4	60	198	38	180	-	2.0	0.9288	206900	"
5	30	76	147	5826	4.26	78.0	0.9158	69260	(ⁿ PrCp) ₂ ZrCl ₂
6	30	96	78	6094	2.02	37.6	0.9210	83840	"
7	60	134	296	4142	6.31	114.8	0.9156	56500	"
8	15	120	21	656	-	4.1	0.9292	151900	"
C 9	30	42	41	2929	5.30	123.6	0.9465	61470	"
10	60	149	18	121	-	1.9	0.9491	220300	(ⁱ PrCp) ₂ ZrCl ₂
C 11	30	139	49	353	0.46	15.7	0.9376	112450	"
12	60	146	62	531	-	0.9	0.9233	216200	(1,3-MeEtCp) ₂ ZrCl ₂
C 13	60	100	88	660	0.31	16.0	0.9197	148200	"
14	30	126	113	2152	0.33	11.1	0.9299	111760	(1,3-Me ⁿ BuCp) ₂ ZrCl ₂
15	60	151	40	199	-	3.9	0.9306	155400	"
C 16	30	137	156	1708	1.27	24.6	0.9150	94100	"
17	60	136	118	813	0.84	47.3	0.9209	90600	Me ₂ Si(THF) ₂ ZrCl ₂

¹I_{gPE}/(I_{gCAT} · h, 150 psi)

- 18 -

CLAIMS

What is claimed is:

1. A catalyst system comprising:
 - 5 a) at least one first component comprising a majority of at least one supported bulky ligand transition metal compound; and
 - b) at least one second component comprising a majority of at least one supported activator.
- 10 2. A catalyst system comprising:
 - a) a catalyst component of at least one first carrier and at least one bulky ligand transition metal compound;
 - b) an activator component of at least one second carrier and at least one activator.
- 15 3. A catalyst system comprising a first component comprising a supported bulky ligand transition metal catalyst compound and a second component comprising separately supported activator for said compound.
4. The catalyst system of any of the preceding claims wherein said bulky


20 ligand transition metal compound is a metallocene.
5. The catalyst system of any of the preceding claims wherein said activator is at least one of an alumoxane or an ionic activator or combination thereof.
- 25 6. The catalyst system of any of the preceding claims wherein said first and second components are supported on a carrier from the group of inorganic oxides, inorganic chlorides, or polymeric compounds or mixtures thereof.
7. The catalyst system of any of the preceding claims wherein no less than 75

30 weight percent of all the bulky ligand transition metal compound within the catalyst system resides on the first component and/or no less than 75 weight percent of all the activator within the catalyst system resides on the second component.
8. The catalyst system of any preceding claim wherein said bulky ligand

35 transition metal compound is represented by the general formulas:

$$(C_5R'_m)_pR''_s(C_5R'_m)MQ_{3-p-x} \text{ and}$$

- 19 -



- wherein M is a Group 4, 5, 6 transition metal, $C_5R'_m$ is an unsubstituted and/or a symmetrically or unsymmetrically substituted cyclopentadienyl, each R' , which can be the same or different is hydrogen, alkyl, alkenyl, aryl, alkylaryl or arylalkyl radical having from 1 to 20 carbon atoms or two carbon atoms joined together to form a part of a C_4 to C_{20} ring, R'' is one or more of or a combination of a carbon, a germanium, a silicon, a phosphorous or a nitrogen atom containing radical substituting on and bridging two $(C_5R'_m)$ rings, or bridging one $(C_5R'_m)$ ring back to M, when $p = 0$ and $x = 1$ otherwise "x" is always equal to 0, each Q which can be the same or different is an aryl, alkyl, alkenyl, alkylaryl, or arylalkyl radical having from 1 to 20 carbon atoms or halogen, Q' is an alkylidene radical having from 1-20 carbon atoms, s is 0 or 1 and when s is 0, m is 5 and p is 0, 1 or 2 and when s is 1, m is 4 and p is 1.
9. The catalyst system of any preceding claims wherein said first component is essentially or substantially free of an activator and/or wherein said second component is essentially free of a bulky ligand transition metal compound.
10. The catalyst system of any preceding claims wherein the weight percent of said bulky ligand transition metal compound in said first component is in the range of from 1 to 10 weight percent based on the total weight of the first component and/or the weight percent of the activator is in the range of 1 to 15 weight percent based on the total weight of the second component, preferably the mole ratio of the transition metal of the bulky ligand transition metal compound of the first component to the metal of the activator of the second component is about 1:50.
11. The catalyst system of any preceding claim wherein said catalyst system further comprises a traditional Ziegler-Natta or other non-metallocene catalyst.
12. A process for polymerizing olefins alone or in combination with one or more other olefins in a reactor, said process comprising polymerizing and/or prepolymerizing in the presence of the catalyst system of any of the preceding claims.
13. The process of claim 12 wherein components (a) and (b) of the catalyst system of claims 1-11 are introduced into the reactor simultaneously, or introduced

- 20 -

into the reactor from different locations in the reactor, or preferably introduced into the reactor mixed together.

14. A method for producing the catalyst system of any one of the preceding
5 claims 1-11 comprising the steps of:
- a) contacting predominantly at least one first carrier with at least one bulky ligand transition metal compound; and separately
 - b) contacting predominantly at least one second carrier with at least one activator for said compound.

INTERNATIONAL SEARCH REPORT

 Int ional Application No
 PCT/US 94/10178

 A. CLASSIFICATION OF SUBJECT MATTER
 IPC 6 C08F4/02 C08F4/605 C08F10/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

 Minimum documentation searched (classification system followed by classification symbols)
 IPC 6 C08F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP,A,0 560 128 (BASF) 15 September 1993 see claims; example ---	1-4, 6-10, 12-14
X	FR,A,2 312 512 (NAPHTACHIMIE) 24 December 1976 see page 1, line 36 - page 4, line 6 see claims; examples ---	1-3, 6, 7, 9, 10, 12-14
A	DATABASE WPI Section Ch, Week 7811, Derwent Publications Ltd., London, GB; Class A, AN 78-20587A & JP,A,53 011 982 (MITSUBISHI PETROCH. KK) see abstract -----	1

☐ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- "&" document member of the same patent family

Date of the actual completion of the international search

24 November 1994

Date of mailing of the international search report

23. 12. 94

Name and mailing address of the ISA

 European Patent Office, P.B. 5818 Patentlaan 2
 NL - 2280 HV Rijswijk
 Tel. (+ 31-70) 340-2040, Tx. 31 651 epo nl,
 Fax: (+ 31-70) 340-3016

Authorized officer

Mettler, R-M

INTERNATIONAL SEARCH REPORT

information on patent family members

Int. Application No

PCT/US 94/10178

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP-A-0560128	15-09-93	DE-A- 4207899 JP-A- 6023273	16-09-93 01-02-94
FR-A-2312512	24-12-76	BE-A- 842241 DE-A, C 2623693 GB-A- 1500868 LU-A- 75016 NL-A- 7605598 US-A- 4035560	26-11-76 02-12-76 15-02-78 20-01-77 30-11-76 12-07-77